

fumasep® FAA

General

The membrane type fumasep FAA is a caustic stable ion exchange membrane with high mechanical stability and good selectivity properties, intended for use in electrodialysis.

Membranes are identified by membrane type and identification number (Lot.-Number). Please refer to this type and identification number in case of queries.

Handling

Handle with care, be sure not to puncture, crease or scratch the membrane, otherwise leaks will occur. All surfaces which may get into contact with the membrane during inspection, storage, pretreatment and mounting must be free of sharp edges or angles.

To control and minimise wrinkling it is recommended to expand membranes before cutting and module assembly by equilibration in the process solution for sufficient time.

After pretreatment do not let the membrane dry out since micro cracks may likely occur during shrinkage. We recommend to expand the membrane in the process solution before cutting and stack assembly.

Storage

Storage for short and medium time scale (hours up to several days) may be done in unsealed containers in 3-5 wt-% NaCl solution or comparable neutral pH electrolytes. For storage over a longer time period a sealed container is recommended using afore said electrolyte with ca. 100 ppm biocide (NaN_3) to avoid biological fouling.

If you have any concerns about storage, chemical stability and pretreatment before proceeding, please feel free to contact us for further information.



Physical and chemical data

fumasep FAA, anion exchange membrane, PEEK reinforced		
selectivity **)	%	>92
electric resistance *)	$\Omega \cdot \text{cm}^2$	< 2
stability		caustic stable
thickness ***)	mm	0,130 –0, 150
ion exchange capacity	meq/g	>1,2
specific conductance	mS/cm	>8 ****)

*) measured in Chlorid form in 0,5 M NaCl @ RT 25°C)

***) determined from membrane potential measurement in a concentration cell 0,1/0,5 M KCl @ 25°C

****) in wet form

*****) determined in Cl⁻ -form in 0,5 NaCl @ RT (30°C)

Please note: The measuring data are not measured directly on the item supplied. The data correspond with the measurement of our quality control.

FuMA-Tech GmbH
-Membranherstellung und Entwicklung-
Am Grubenstollen 11
D-66386 St. Ingbert/Saar
Telephon: +49-(0)-6894-9265-0
Fax: +49-(0)-6894-9265-99
e-mail: info@fumatech.de